

# HellFire® Concrete Coating

(Formula 2)

## Product Description

**HellFire® Concrete Coating** is a single component, proprietary, moisture cured, aromatic urethane fortified with a metallic additive that exhibits outstanding characteristics exceeding competitive products. **HellFire® Concrete Coating** has excellent chemical resistance, heat resistance and substrate penetration. **HellFire® Concrete Coating** offers the user easy installation and fast recoats coupled with excellent protection. **HellFire® Concrete Coating** can be used in warehouses, garages, auto-service centers, utility rooms, "back of house" floors, steel/metal (clean and oxidized) and marine-vessel surfaces. **HellFire® Concrete Coating** was formulated for extreme performance and protection under the worst of conditions.

## Features and Benefits

Long Pot-Life  
Single Component (no a&b to mix)  
**Extreme Wear, Chemical, Fuel & Solvent Resistance**  
Fast Cure & Recoats  
Outstanding Heat & UV Resistance  
Saber-Gray Appearance  
Low Prep- surface dependent

## Recommended Applications

**HellFire® Concrete Coating** is recommended for all new and existing interior concrete surfaces requiring a no-nonsense chem/wear resistant, waterproof and protective maintenance coating. Interior surfaces: garages, warehouses, manufacturing floors, loading docks, marine environments, laboratories, chemical splash zones and vehicle-service centers. *Exterior surfaces: vehicle chassis, equipment chassis, marine vessels, metal surfaces (clean or oxidized).* *This is NOT a decorative product. Consider our epoxy or Nohr-S® Polyurea product for more esthetically pleasing finishes.*

## Technical Data

Solids: 52%	(additional information found on -fact sheet-)
Pot-Life: 1-1.5 Hours(keep covered when not using)	Solvent & Fuel Resistance: Excellent
VOC Level: 426 gms/liter	Finish: low gloss
Recoat time: 2-3 Hours	Appearance: opaque
Foot Traffic: 12 hours	Abrasion Resistance: Excellent
Wheel Traffic: 72 hours	Concrete Adhesion: Excellent
Film Thickness: 2-3.0 dft per coat	Application temp: 35-85 deg f.

## Coverage Rates

Use a 400 psqft average, per coat, when applying our recommended (3) coats.  
HellFire is thin, (3) coats offer the best appearing finish

## Shelf-Life

**HellFire® Concrete Coating** has a one-year shelf life in an unopened container. Once opened and resealed the product may "weld" the lid closed if not cleaned properly before re-sealing.

## Packaging

1.0 quart and 1.0 gallon unit, AVAILABLE IN 5 gallon buckets - 10 bucket minimum order, contact us.

## Instructions for Use

Legacy Industrial

570 Lake Cook Rd Ste 300, Deerfield, IL 60015

1-888-652-0333 - sales@legacyindustrial.co - www.legacyindustrial.co

**PREP:** Before application the receiving surface must be deemed structurally and mechanically sound, clean, and dry. Proper surface preparation is required for decorative concrete, thin film flooring systems or sealer/finish coatings. This is best achieved with mechanical sanding or acid etching following directions found on Legacy Industrial's website in "Downloads" [www.legacyindustrial.co](http://www.legacyindustrial.co) . We recommend the surface be porous. All receiving surfaces must be free of previous coatings, sealers, curing compounds, water repellants, laitance, efflorescence, oils, fats, grease, waxes, residues from cleaning compounds, non-visible soluble salts, and any other impediments to adhesion. Always check for potential bond breakers. One method entails pouring a slight amount of water on the concrete in random areas. If the water is absorbed into the concrete and leaves it wet, the substrate is porous and thus acceptable for coating. If water beads up, this indicates a bond breaker is still present or the concrete is too smooth and further surface preparation steps are necessary, such as additional mechanical sanding or grinding. Previously coated surfaces must be diamond ground. This will also necessitate additional coats of Hellfire® for a favorable finish. The rising moisture vapor emission rate must not exceed 3 pounds per 1,000 square feet (3 lb/1,000 ft²) over a 24-hour period as measured by the calcium chloride test method, ASTM F 1869. The relative humidity in the slab must not exceed 80 percent. Steel or oxidized metal surfaces must be reasonably cleaned of scale and oil free prior to use.

**MIXING:** Mix this product using a clean, dry, working bucket. Stir gently using a mechanical stirrer attached to a low speed cordless drill, avoiding over-mixing or creating a vortex that would introduce moisture. Stir until material has a non-streaking appearance. No induction time is required prior to use. Soft-Skid non-skid additive can be used, mix in last coat of product. Re-mix product as needed during application.

**APPLICATION:** Apply using roller. The roller must be an industrial grade, phenolic-resin core with a synthetic nap, 3/8 inch nap, 9" or 18" width. It should be dipped and rolled never dumped on the surface. Due to the metallic additive in this product it is important to place enough product on the roller and back-roll often to avoid roller marks. This product is not recommended for flooring application using spray atomization. Follow all safety and personal protection advice, listed on the product can. SDS is available upon request. This product is best applied in thin coats. Never over-apply or apply too thick or you can expect fracturing, bubbling and/or failure. Additional thin coats are acceptable. **Recoats that fall within (6) hours of initial application:** Apply additional coats within 6 hours of the previous coat for best adhesion and without further prep. Hellfire® can be top coated with Legacy Industrial's HellFire® Clear-Coat at this time as well. **Re-coats that fall outside the recoat window:** De-gloss coating with 120 grit screen or Black Abrasive Stripper Pad, wipe with denatured alcohol and apply coating. **Clear-Coats that fall outside the recoat window:** De-gloss coating with 120 grit screen or Black Abrasive Stripper Pad, wipe with denatured alcohol. Apply (1) coat of Hellfire®, allow to dry (tack-free) and within (6) hours apply (1) coat of HellFire® Clear-Coat

**WARNING:** Omitting the coat of Hellfire® will result in an uneven coloration.

### Clean-Up

Tools: Xylene or Acetone while coating is still wet. Skin: Immediately clean with soap and water. Once dried the product will wear off in approx. 10 days. **WEAR GLOVES!**

### Product Removal

This product cannot be removed by any stripper. It can only be removed using mechanical means once cured.

### Precautions and Limitations

Restrict the use of the floor to wheeled traffic and non-harsh chemicals after 24 hours has passed. Keep the floor dry for this period. Always test cleaners prior to use. High humidity can increase the curing speed dramatically. Open cans that are re-sealed will prove very difficult to open. Decorative flake can be used but will sit proud of the coating, *consider our epoxy or Nohr-S polyurea product if decorative flake is required.* Read the container label warning and Safety Data Sheet for important health and safety information prior to use for details on the safe handling and use of these products. Proper ventilation and PPE is encouraged during the use of this product. This product was formulated for high chem and wear resistance and less for decoration. *Consider our epoxy or Nohr-S polyurea product if a more esthetically pleasing finish is required.*

### NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our product is manufactured to the specifications as stated her or in other publications. All other information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Any use or application other than recommended herein is the sole responsibility of the user. Uncured epoxy resins, polymers and their curing agents may be **ALKALINE, TOXIC or BOTH**, depending on the particular system. They may cause **ALLERGIC REACTIONS or HYPERSENSITIVITY REACTIONS.** **BEFORE USING any material, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.**

COPYRIGHT 1/1/11 Legacy Industrial, A Clean Seal LLC Company or Legacy Industrial Corp.