

OUTSIDE DIAMETER AND THICKNESS

CHARLOTTE
PIPE AND FOUNDRY COMPANY®

CPVC Schedule 80 Pipe



>> **CORZAN®** CPVC Schedule 80 Pipe, Type IV, Grade 1

ASTM D 1784 & ASTM F 441

CPVC SCHEDULE 80 (LIGHT GRAY)			PLAIN END		CPVC 4120	
PART NO.	NOM. SIZE	UPC # 611942-	AVG. OD (IN.)	MIN. WALL (IN.)	MAX WORK PRESSURE AT 23° C OR 73° F	WT. PER 100 FT. (LBS.)
CPV 11002	1/4"x20'	04931	.540	.119	1130 PSI	10.9
CPV 11003	3/8"x20'	04943	.675	.126	920 PSI	15.0
CPV 11005	1/2"x20'	04787	.840	.147	850 PSI	22.1
CPV 11007	3/4"x20'	04788	1.050	.154	690 PSI	30.0
CPV 11010	1"x20'	04789	1.315	.179	630 PSI	44.2
CPV 11012	1 1/4"x20'	04790	1.660	.191	520 PSI	61.0
CPV 11015	1 1/2"x20'	04791	1.900	.200	470 PSI	73.9
CPV 11020	2"x20'	04792	2.375	.218	400 PSI	102.2
CPV 11025	2 1/2"x20'	04793	2.875	.276	420 PSI	155.9
CPV 11030	3"x20'	04794	3.500	.300	370 PSI	208.6
CPV 11040	4"x20'	04795	4.500	.337	320 PSI	304.9
CPV 11060	6"x20'	04796	6.625	.432	280 PSI	581.5
CPV 11080	8"x20'	04797	8.625	.500	250 PSI	882.9

NSF Listed. Meets All Requirements of ASTM D 1784 and ASTM F 441.

CPVC piping products are not recommended for use with compressed air or gases.

Corzan is a registered trademark of The Lubrizol Corporation.

You can't beat the system.®